



TRETFORD TILE SPECIFICATION

DESCRIPTION

Tretford Tile is made from carded fibres formed into a continuous corrugation and bonded to a 100% post-consumer recycled Eco PET backing.

MATERIALS

Pile composition of carpet: 70% Goat Hair (512 Dapple Grey, 538 Silver Birch and 587 Double Cream are manufactured using undyed goat hair), 30% Nylon.

WARRANTIES

Wear Guarantee and a Lifetime Anti-Ravel/Non-Zipper Guarantee. BS EN1307:2005 Class 33 LC2 Heavy Commercial Use.

DIMENSIONS & WEIGHT Size: 50cm x 50cm Packing: 5m² per box Thickness: 9.1mm Weight: ca. 3.8kg / sq.m.

FLAMMABILITY

BS 4790:1987 Mean radius of burning: 25mm Class: low

BS EN ISO 11925:2002, BS EN ISO 9239-1: Euroclass Cfl-s1

Critical radiant flux test: ANSI/ASTM E648 result category 1

EN ISO 9239-1:2003: CHF value: mean 5.1 kW/m² loose laid and direct stick.

Conclusion: Suitable for all commercial / contract installations including Institutional, Commercial and Public Buildings.

THERMAL INSULATION (ISO 8302:1991)

Thermal resistance (R-value): 0.09 m² K/W

Conclusion: Satisfactory thermal properties for normal underfloor heating.

ELECTRICAL PROPERTIES / STATIC

ISO 6356:2000: -1.3kV, BS EN 14041:2004: Classified as antistatic

AATCC TM 134 Step test: 2.7kV, Scuff test: 3.0 kV - Suitable for commercial use

IBM and ICL Electrical Resistance: Tested at 40% RH and 20°C - Passed

Recommendation: To prevent discomfort a minimum of 40% RH should be maintained.

LOSS IN THICKNESS AFTER DYNAMIC LOADING (BS 4052:1987)

Thickness loss % after 1000 Impacts: 13.33%

DIMENSIONAL STABILITY (BS EN 986:2005) Dimensional Stability test requirements: -0.2% - +0.2% - Passed.

COLOUR FASTNESS (BS 1006:1990)

To light - colour change: 5-6 very slight to none To water spotting - colour change: 4 very slight

To carpet shampoo - colour change: 3-4 slight To rubbing - colour change: 4 very slight.

IMPACT INSULATION (EN ISO 140-8:1998)

Centre band frequencies (HZ)	200	400	800	1000
Test 1 bare concrete (dB)	63.7	66.1	66.3	66.2
Test 2 bare concrete with tretford (dB)	53.7	42.0	28.1	22.0
Regulation Requirements (dB)	66	66	64	63

Conclusions: This carpet meets the requirements of the building regulations by a useful margin.

SOUND ABSORPTION (EN ISO 354:2003)

Sound absorption grade (EN ISO 11654:1997) is 0.25

	125	250	500	1000	2000	4000 Hz
Carpet	0.02	0.05	0.14	0.29	0.27	0.35

MOTHPROOFING (BS 4797:1972) (SIS 650220)

tretford tile is moth-resistant to the following standards:

European Standards.

CASTOR CHAIR PROTECTORS (for appearance retention purposes)

Recommended with 3 colours. Mandatory with 1 and 2 colours.



2009/533

JOSEPH HAMILTON & SEATON
RELAY PARK, RELAY DRIVE, TAMWORTH STAFFORDSHIRE, B77 5PR

TELEPHONE: (01827) 831400 TELEFAX: (01827) 831401
EMAIL: sales@jhscarpets.com

Registered Office: Gorsey Lane Coleshill Birmingham B46 1JU England HFD Ltd Registered in England and Wales No. 2674152